

ASTM A514 steel plate/sheet High yield strength for cold forming steels

ASTM A514 steel plate/sheet,EN10149 A514 steel plate/sheet, under ASTM standard, we can regard A514 steel plate/sheet as high yield strength steels for cold-forming steels.

ASTM A514 is mainly used as high yield strength steels for cold-forming steels.The ASTM A514 steel is equivalent to DIN QStE690TM, NFA E690D, EN S700MC and BS 75F70 steel grades.

A514 ASTM Number:1.8974	Comparision of steel grades	
	SEW092	QStE 690TM
	NFA36-231	E690D
	UNI8890	-
	EN 10149-2	S700MC
	BS1449	75F70

Chemical Composition of A514 steel,by %

Grade	C max	Si max	Mn max	P max	S max	AL max	Nb max	V max	Ti max	Mo max	B max
A514	0.12	0.6	2.1	0.025	0.015	0.015	0.09	0.2	0.22	0.5	0.005

Mechanical Properties of A514 steel

Nominal thickness(mm)	-
ReH-Minimum yield strength(Mpa)	700

Nominal thickness(mm)	-
Rm-Tensile strength(Mpa)	750-950

Nominal thickness(mm)	From3
A-Minimum elongation Lo=5,65√So(%)	12

Nominal thickness(mm)	to3
A-Minimum elongation Lo=Lo=80mm(%)	10

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.



BEBON

BebonChina.com

Henan BEBON international co.,ltd

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.