

ASTM A572Gr.65 steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steels

ASTM A572Gr.65 steel plate/sheet, ASTM A572Gr.65 steel plate/sheet, under ASTM standard, we can regard A572Gr.65 steel plate/sheet for Fine-grain structural steels, thermomechanically rolled steel.

ASTM A572Gr.65 is a technical delivery conditions for thermomechanical rolled weldable fine grain structural steels. S means the structural steel, M means the delivery condition. Capital letter L for the quality with specified minimum values of values of impact energy at temperature not lower than -20 degree.

A572Gr.65 ASTM Number:1.8827	Comparision of steel grades	
	SEW 083	StE 460 TM
	NFA 36-201	E 460 R
	UNI 7382	Fe E 460 KGTM
	BS 4360	-
	EN10113-3	S460M

Chemical Composition of A572Gr.65 steel

Grade	C max	Si max	Mn max	P max	S max	N max	AL max	Nb max	V max	Ti max	Cr max	Ni max	Mo max	Cu max	CE V max
A572 Gr.65	0.16 %	0.60 %	1.70 %	0.03 %	0.02 5%	0.02 5%	0.02 %	0.05 %	0.12 %	0.05 %	0.30 %	0.80 %	0.20 %	0.55 %	0.48 %

Mechanical Properties of A572Gr.65 steel

Temperature	-10	0	20
Notch impact test. Min. absorbed energy	43	47	55

Nominal thickness(mm)	to 16	16-40	40-63	63-80	80-100	100-120
ReH-Minimun yield strength(Mpa)	460	440	430	410	400	385

Nominal thickness(mm)	to 40	40-63	63-80	80-100	100-120
Rm-Tensile strength(Mpa)	540-720	530-710	510-690	500-680	490-660
Nominal thickness(mm)	-				
A-Minimum elongation Lo=5.65√So(%)	17				

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.