



EN 10083 C50 steel plate high carbon steel

C50 steel plate, EN 10083 C50 steel plate, under EN 10083 standard, we can regard C50 steel plate as high carbon steel.

C50 steel plate is one mainly of high carbon steel,EN 10083 C50 steel plate is one of the higher carbon content (0.47-0.55) steels.It is equal to DIN C50,JUS Č.16301 and NF AF70C55.

<p>C50 EN 10083-2 Number: 1.0540</p>	Comparison of steel grades	
	JUS	Č.16301
	DIN	C50
	BS	-
	GOST	-
	AISI	-
	UNI	-
	NF	(AF70C55)

Chemical analysis -% by mass * of C50 steel

Chemical elements	C	Si max	Mn	P max.	S max.	Cr max.	Mo max.	Ni max.	Cr+Mo+Ni max.
% by mass	0,47-0,55	0,40	0,60-0,90	0,045	0,045	0,40	0,10	0,40	0,63
Permissible deviation	± 0,02	+ 0,03	± 0,04	+ 0,005	+ 0,005	+ 0,05	+ 0,03	+ 0,05	-

At the option of the manufacturer the elements aluminium, titanium, vanadium and niobium may be added singly or in combination for grain size control purposes.

Elements not quoted in table shall not be added to the steel without the agreement of the purchaser, except for

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com http://www.bebonchina.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.



the purpose of finishing the heat.

Mechanical properties in the normalized and normalized and tempered conditions of C50 steel

Diameter in mm		Thickness of ruling section t_R			
		$t_R \leq 100\text{mm}$	$100 < t_R \leq 250\text{mm}$	$250 < t_R \leq 500\text{mm}$	$500 < t_R \leq 1000\text{mm}$
$R_e \text{ min (N/mm}^2\text{)}$		320	290	-	-
$R_m \text{ min (N/mm}^2\text{)}$		610	590	-	-
A % min.	l-longitudinal	14	14	-	-
	tr -transverse	-	-	-	-
KV min * (J)	l-longitudinal	-	-	-	-
	tr -transverse	-	-	-	-

1N/mm²=1MPa

Heat treatment conditions

Quenching Temperature, °C	Cooling medium	Tempering Temperature, °C	Normalizing Temperature, °C
810 to 850	Oil or water	550 to 660	830 to 870

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:<http://www.shipbuilding-steel.com> <http://www.bebonchina.com>

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.