

DIN 17200 C60 steel plate high carbon steel

C60 steel plate, DIN 17200 C60 steel plate, under DIN 17200 standard, we can regard C60 steel plate as high carbon steel.

C60 steel plate is one mainly of high carbon steel, DIN 17200 C60 steel plate is one of the higher carbon content (0.60%) steels. It is more difficult to fabricate than the lower carbon grades.

C60 DIN 17200 Number:1.0601	Comparision of steel grades	
	JIS G 4051	S 58 C
	EN10083	C 60
	NFA 33-101	-
	UNI 7846	-
	BS 970	070 M 60
	UNE 36011	-
	SAE J 403-AISI	1060

Chemical Composition of C60 steel

Grade	C(%)min-max	Si(%)min-max	Mn(%)min-max	P(%)max	S(%)max	Cr(%)min-max
C60	0.57-0.65	0.15-0.35	0.60-0.90	0.025	0.025	0.20-0.40

Mechanical Properties of C60 steel

Grade	Condition	Yield Strength R ^o (Mpa)	Tensile Strength Rm (Mpa)	Elongation A5(%)	Hardness HRC	Quenching Temperature (°C)	Bendability	Nominal Thickness,t 1.95mm≤t≤10.0 mm	
								Rolled	Annealed
C60	Rolled	540	875	17	63	800	Min.recommended Bending radius (≤90°)	3.0×t	1.0×t
	Annealed	370	580	29	60	840			
	Water-quenched		2670						
	Oil quenched		2430						

Bebon steel — **The most professional exporter on shipbuilding steel**

E-mail:bb@bebonchina.com

Tel:0086-371-86151527

MSN:bebonchina@hotmail.com

Fax: 0086-371-86011881

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.

Skype: bebonchina

www.bebonchina.com

www.shipbuilding-steel.com

www.steel-plate-sheet.com