

**ASTM 070XLK steel plate/sheet High yield strength for cold forming steels**

ASTM 070XLK steel plate/sheet, ASTM 070XLK steel plate/sheet, under ASTM standard, we can regard 070XLK steel plate/sheet as high yield strength steels for cold-forming steels.

ASTM 070XLK is mainly used as high yield strength steels for cold-forming steels. The ASTM 070XLK steel is equivalent to SEW092 QStE500TM, NFA E490D, UNI FeE490TM and EN S500MC steel grades.

070XLK ASTM Number:1.0984	Comparision of steel grades	
	SEW092	QStE 500TM
	NFA36-231	E490D
	UNI8890	FeE490TM
	EN 10149-2	S500MC
	BS1449	-

Chemical Composition of 070XLK steel, by %

Grade	C max	Si max	Mn max	P max	S max	AL max	Nb max	V max	Ti max
070XL K	0.12	0.50	1.7	0.025	0.015	0.015	0.09	0.2	0.15

Mechanical Properties of 070XLK steel

Nominal thickness(mm)	-
ReH-Minimum yield strength(Mpa)	500

Nominal thickness(mm)	-
Rm-Tensile strength(Mpa)	550-700

Nominal thickness(mm)	From3
A-Minimum elongation Lo=5,65√So(%)	14

Nominal thickness(mm)	to3
A-Minimum elongation Lo=Lo=80mm(%)	12

**Bebon steel — The most professional exporter on shipbuilding steel**

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebonchina@hotmail.com

Skype: bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.