

EN 10083 C40 steel plate high carbon steel

C40 steel plate, EN 10083 C40 steel plate, under EN 10083 standard, we can regard C40 steel plate as high carbon steel.

C40 steel plate is one mainly of high carbon steel, EN 10083 C40 steel plate is medium Carbon Steels are similar to low carbon steel except that the carbon ranges from 0.30 to 0.60% & the manganese from 0.50 to 1.65%. Increasing the carbon content is approximately 0.5% with an accompanying increase in manganese allows medium carbon steels to be used in the quenched & tempered conditions. This steels are of particular importance because of unique combination of strength & toughness after heat treat treatment.

		Comparison of steel grades	
C40		JUS	Č.14341
EN 10083-2		DIN	C40
Number: 1.0511		BS	080M40, EN8
		GOST	40
		AISI	1040
		UNI	C40,
		NF	(AF60C40), (1C40)

Chemical analysis -% by mass

Chemical elements	C	Si max.	Mn	P max.	S max.	Cr max.	Mo max.	Ni max.	Cr+Mo+Ni max.	
% , by mass	0,37-0,44	0,40	0,50-0,80	0,045	0,045	0,40	0,10	0,40	0,63	-
Permissible deviation	± 0,02	+ 0,03	± 0,04	+ 0,005	+ 0,005	+ 0,05	+ 0,03	+ 0,05		-

At the option of the manufacturer the elements aluminium, titanium, vanadium and niobium may be added singly or in combination for grain size control purposes.

Elements not quoted in table shall not be added to the steel without the agreement of the purchaser, except for the purpose of finishing the heat.

Mechanical properties in the normalized conditions

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebонchina@hotmail.com

Skype: bebonchina

Web:<http://www.shipbuilding-steel.com> <http://www.bebonchina.com>

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.

		Thickness of ruling section t_R			
Diameter in mm		$t_R \leq 100\text{mm}$	$100 < t_R \leq 250\text{mm}$	$250 < t_R \leq 500\text{mm}$	$500 < t_R \leq 1000\text{mm}$
$R_e \text{ min } (\text{N/mm}^2)$		290	260	-	-
$R_m \text{ min } (\text{N/mm}^2)$		550	530	-	-
A % min.	l-longitudinal	17	17	-	-
	tr -transverse	-	-	-	-
KV min * (J)	l-longitudinal	-	-	-	-
	tr -transverse	-	-	-	-

 $1\text{N/mm}^2=1\text{MPa}$
Heat treatment conditions

Quenching Temperature, $^{\circ}\text{C}$	Cooling medium	Tempering Temperature, $^{\circ}\text{C}$	Normalizing temperature, $^{\circ}\text{C}$
830 to 870	Water or oil	550 to 660	850 to 890

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax: 0086-371-86011881

MSN:bebонchina@hotmail.com

Skype: bebonchina

Web:<http://www.shipbuilding-steel.com> <http://www.bebonchina.com>

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.