



EN10113 S460ML steel plate/sheet

S460ML EN 10113-3 Number:1.8838	Comparision of steel grades	
	SEW 083	TStE 460 TM
	NFA 36-201	E 460 FP
	UNI 7382	Fe E 460 KGTM
	BS 4360	55 EE
	ASTM	A 572 Gr.65

Chemical Composition of EN S460ML steel

Grade	C max	Si max	Mn max	P max	S max	N max	AL max	Nb max	V max	Ti max	Cr max	Ni max	Mo max	Cu max	CEV max
S420 ML	0.16 %	0.60 %	1.70 %	0.025 %	0.02 %	0.025 %	0.02 %	0.05 %	0.12 %	0.05 %	0.30 %	0.80 %	0.20 %	0.55 %	0.48 %

Mechanical Properties of EN S460ML steel

Temperature	-50	-40	-30	-20	-10	0	20
Notch impact test. Min. absorbed energy	27	31	40	47	51	55	63
Nominal thickness(mm)	to 16	16-40	40-63	63-80	80-100	100-120	
ReH-Minimun yield strength(Mpa)	460	440	430	410	400	385	
Nominal thickness(mm)	to 40	40-63	63-80	80-100	100-120		
Rm-Tensile strength(Mpa)	540-720	530-710	510-690	500-680	490-660		
Nominal thickness(mm)	-						
A-Minimum elongation Lo=5,65√So(%)	17						

Bebon steel — The most professional exporter on shipbuilding steel

Tel:0086-371-86151527

E-mail:bb@bebonchina.com

Fax:0086-371-86011881

MSN:bebonchina@hotmail.com

Skype:bebonchina

Web:http://www.shipbuilding-steel.com

Oficina Dir: 2801 B# International enterprise center Zhengzhou city in China.